

Ferro Manganese High Carbon

Grade	Mn	C	S	P	Si
	min		max		max
	%	%	%	%	%
WFMHC-A	75-80	6-8	0.03 - 0.05	0.25	0.5
WFMHC-B	70-75	6-8	0.05	0.3 – 0.4	1.5

Granulometry: 20 – 80 mm (90%)

Ferro Silico Manganese

Grade	Mn	Si	C	S	P
	%	%	%	%	%
WFSM-A	65-70	16-18.50	2	0.05	0.2
WFSM-B	60-65	14-17	2	0.05	0.4

Ferro Vanadium

Grade	V	C	S	P	Si	Al
	%	%	%	%	%	%
WFV-A	80 Min	0.15	0.05	0.05	1.50	2.0
WFV-B	58-62	0.10	0.05	0.05	1.50	2.0
WFV-C	50-55	0.10	0.05	0.05	1.50	2.0